

ArChine Polymer Quenchant E

Product Description

ArChine Polymer Quenchant E is a nonflammable polymeric quenchant and is aqueous solutions of a liquid organic polymer with corrosion inhibitor. The organic polymer is soluble in water. At temperatures above 74°C (165°F), however, the polymer separates from water as an insoluble phase.

ArChine Polymer Quenchant E is suitable for the hardening of following application.

- ☆ Large alloy parts from tilt-top, car-bottom and pit furnaces
- ☆ Forged parts that are quenched directly from the forge
- ☆ Sensitive alloys and shapes heated by induction
- ☆ Parts processed from continuous and batch-furnace operations employing gas-fired, neutral, and carburizing-carbonitriding atmospheres requiring oil quenching rates.

Typical Physical Property

	ArChine Polymer Quenchant E
Weight per Gallon @ 20°C, l	8.94
Specific Gravity at 20/20°C	1.075
Pour Point, °C (°F)	-20°C (-4°F)
Viscosity 40°C, cSt	380
PH Value	9~11
Rust Inhibition, ASTM D 665A	Pass
Flash Point, Cleveland Open Cup, ASTM D 92	None

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com