

## ArChine Comptek EMG 39

### Food Grade Fully Synthetic Compressor Oil

#### Product Description

ArChine Comptek EMG 39 is developed from a unique of PAG and POE, which together form an exceptional coolant and act to reduce deposit formation. It is a long life lubricant formulated with rust and oxidation inhibitors.

ArChine Comptek EMG 39 offers excellent heat transfer properties, high flash point, low volatility, low evaporation and outstanding hydrolytic stability. It will not form varnish deposits like petroleum or PAO oils.

#### Features and Benefits

- Wide temperature range
- Cost effective: Extended oil change intervals
- Eliminates deposit formation
- High flash point means reduced fire hazards
- High viscosity index means less change over wide temperature range
- Excellent oxidative and thermal stability
- Low pour point
- Low coefficient of traction
- Good demulsability when compared to other polyglycol lubricants

#### Applications

#### Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Address: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai 200235 P.R.China

Telephone helpline: (86)15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

ArChine Comptek EMG 39 can be recommended for use in oil-flooded rotary compressors operating at high air pressures and discharge temperatures--vane, lobe, and screw—that specify a polyglycol lubricant.

ArChine Comptek EMG 39 is NSF H-1 registered for use in federally inspected meat and poultry plants. Complies with FDA 21 CFR 178.3570 Lubricants with incidental food contact.

**Typical Properties\***

ArChine Comptek EMG 39	Typical Value
Appearance	light yellow transparent liquid
Density@ 20°C, g/cm <sup>3</sup>	0.951
Viscosity@ 40°C, mm <sup>2</sup> /s	40.0
Viscosity@ 100°C, mm <sup>2</sup> /s	8.26
Viscosity Index	188
Flash Point, °C (open cup)	252
Fire point, °C	278
Pour Point, °C	-51
Foaming Characteristics 24°C,	30/0
Copper Strip Corrosion,, 100°C/3hr, grade	1

\*Typical data shall not be used as product specifications.

**Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai  
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)