

Shanghai PingYiao Trading CO., Ltd.

ArChine Foodtech AC 2

"Food Grade Grease"

GENERAL:

ArChine Foodtech AC 2 is multi-purpose and high-temp food grade grease designed specifically for lubrication of the wide range of applications in the food industry. This grease is formulated with aluminum complex thickener and other permitted ingredients including base oils and performance additives to meet the stringent requirements of the food industry. This grease has high load carrying capabilities, rust preventative properties, and excellent water resistance.

ArChine Foodtech AC 2 is NSF H1 registered food grade grease formulated specifically for the increasing demands in the beverage and food packaging and processing industries and is an affordable solution to the increasing food machinery lubrication prices. It has high quality and reliable performance specifically designed to meet general and multi-purpose food grad plant lubrication needs.

ArChine Foodtech AC 2 contains a high performance EP additive package providing great extreme pressure and anti-wear protection. The aluminum complex thickener also provides the grease with great resistance to water washout and is thermally stable for use over a wide range of operating temperatures.

FEATURES:

- NSF H1 Food Grade Grease
- Good Extreme Pressure & Rust Protection
- Excellent Water Resistance
- Excellent High Temperature Properties

BENEFITS:

- Provides superior load & rust protection for bearings
 - It works effectively under water borne applications of the food processing industry
- Designed to work effectively in the temperature

TYPICAL PROPERTIES:

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533 Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com



Shanghai PingYiao Trading CO., Ltd.

| | NLGI Grade | ASTM D 217 | 2 |
|--|----------------------------------|-------------|------------------|
| 1. 2. | Color | Visual | White |
| 3. | Worked Penetration | ASTM D 217 | 285 |
| 4. | Drop Point, °F | ASTM D 2265 | + 450 |
| 5. | Viscosity @ 40°C, cSt | | 112 |
| 6. | Viscosity @ 100°C, cSt | ASTM D 445 | 11.0 |
| 7. | Viscosity @ 100°F, SUS | | 580 |
| 8. | Viscosity @ 210°F, SUS | | 69.0 |
| 9. | Type of Thickener | - | Aluminum Complex |
| 10. | Four Ball Weld Load, kg | ASTM D 2783 | 250 |
| 11. | Timken OK Load, lbs | ASTM D 2509 | 45 |
| 12. | Water Washout, wt % loss @ 175°F | ASTM D 1264 | 3.5 |
| 11. Timken OK Load, lbs ASTM D 2509 45 12. Water Washout, wt % loss @ 175°F ASTM D 1264 3.5 | | | |

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250 Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com