

## Shanghai PingYiao Trading CO., Ltd.

# **ArChine SynChain FEC 320**

## Food Grade Polyol Ester Chain oil

### **Product Description**

ArChine SynChain FEC 320 is full synthetic food grade polyol ester chain oil. The product is formulated with high-performance additives, and can provide longer life and higher operating temperature.

ArChine SynChain FEC 320 is non-toxic and non-hazardous, and is suitable for most chain lubrication requirements found in the "clean" industries such as food, beverage, pharmaceutical and personal care products. It has high viscosity index, thermal stability and oxidation stability.

#### **Features and Benefits**

- Superior load and wear properties
- Excellent oxidative and thermal stability
- Reduced sludge and deposit formation
- Good water and rust resistance
- Low volatility, high solvency & low maintenance
- Non-toxic and non-hazardous
- Uniform and complete coverage

#### **Application**

ArChine SynChain FEC 320 is a NSF H1 food grade registered product that meets all regulations set out by the FDA (21 CFR 178.3750) and is approved for incidental contact with food in and around food processing area.

Typical application in the food and beverage industry include:

- Bakery Oven chains
- Tenter Frame Oven Chains

#### **Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533 Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai

200235 P.R.China

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com



## Shanghai PingYiao Trading CO., Ltd.

- Roller Ball Bearing Chains on Oven Conveyers
- Pin/Roller Chains on Tunnel & Tray Ovens
- Beverage Can Lines
- Lithographic Chains
- Paint Oven Chains
- Fiberglass Production
- Cement Plants

### **Typical Properties\***

ArChine SynChain FEC 320	ISO 320
Appearance	Light yellow transparent liquid
Density@ 20°C, g/cm <sup>3</sup>	0.963
Viscosity@ 40°C, mm²/s	324.9
Viscosity@ 100°C, mm²/s	23.23
Viscosity Index	90
Flash Point, °C (open cup)	300
Fire point, °C	322
Pour Point, °C	-21
Copper Strip Corrosion, 100°C/3hr, grade	1
Evaporation Loss@250°C, 24hr, %	26.42
Noack, 1hr, %	0.78
Operating temperature, °C	250

<sup>\*</sup>Typical data shall not be used as product specifications.

#### **Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533 Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai

200235 P.R.China

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: <a href="https://www.pingyiao.com">www.pingyiao.com</a> E-mail: <a href="mailto:info@pingyiao.com">info@pingyiao.com</a>