

ArChine Foodrance WAC 0 PTFE

Grease Appropriated for Food Processing Industries

NSF Registration No.: 145474 **Place of Origin:** France

Color		White
Appearance		Smooth
Nature of soap		Al. complex
NLGI Grade		0
Worked Penetration	0.1mm	355-385
Dropping Point	°C	≥210
4-ball welding	Kg	200
4-ball wearing	mm	≤0.6
Specific additive		PTFE
Nature of base oil		White oil
Viscosity of base oil at 40°C	cSt	180
Viscosity of base oil at 100°C	cSt	18
Viscosity Index		110
Density at 15°C	g/cm ³	0.890
Temperature of use	(continuously)	- 15°C to 130°C

PROPERTIES

- Lubricating performance reinforced by the addition of additives that improve the rubbing coefficient.
- Very good protection against oxidation, corrosion and wearing.
- Excellent resistance under high pressures.
- Neutral with joints.
- Very good performance under water pressure.
- NSF H1, Halal and Kosher approved.

USES

- With its formulation and its wide range of use ArChine Foodrance WAC 0 PTFE has a vast range of applications in food industries:
- Loaded bearings of conveyors.
- Plain bearings subject to high temperatures.
- Bearings, joints and gaskets, chains, varied articulations of all kinds and all brands where it is

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

recommended to use grease in strict conditions: high temperatures, presence of water.

NLGI 0 is mainly used for specific centralized lubrications, reducers, gears where it is recommended to use that grade.

Shanghai PingYiao Trading CO., Ltd.

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com