

# **ArChine Arcanticorrosive 120**

## **Description**

ArChine Arcanticorrosive 120 is an architecture anticorrosive grease. this product contains many additives, and the base oil is mineral oil.

ArChine Arcanticorrosive 120 has many advantages, for example: long life, lubricant, EP performance, water resistant, and compatibility with plastic. This product can be used for producting steel and wire rope, it can meet with lubricanting and anti-rust.

After hear, ArChine Arcanticorrosive 120 did not have bubble and emulsification.

When used at a loe temperature, it had good paintability.

## **Application**

ArChine Arcanticorrosive 120 designed for producting steel and wire rope.

Operation temperature: -20°C~120°C

#### **Technical Data**

ArChine Arcanticorrosive 120	Unit	Test method
Worked penetration, 0.1mm	265-295	GB/T 269
Drop point, °C ≥	160	GB/T 4929
Water content, %	Mark	GB/T 512
Oil separation (100°C, 24h), % ≤	8.0	SH/T 0324
Corrosiveness to steel (45# steel, 100°C, 24h)	Qualified	SH/T 0331
Evaporation (99°C, 22h), % ≤	2.0	GB/T 7325
Cryogenic property, (-40°C, 30min)	Qualified	SH/T 0387
Humidity cabinet test (45#steel, 30d) grade, ≤	2	GB/T 2361
Salt spray test (45#steel, 30d) grade, ≤	2	SH/T 0081
Oxidation stability (99°C, 100h, 0.785MPa)		
A: Pressure Drop, Mpa ≤	0.070 1.0	SH/T 0325 GB/T 264

#### **Distributor Wanted**

#### **Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250 Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com



## Shanghai PingYiao Trading CO., Ltd.

B: Acid number, mgKOH/g, ≤		
Double-pipe compatibility (65°C, 40d)		
A: oil absorption,%, ≤	10	HG 2-146
B: rate of changge of tensile strength, ≤	30	GB 1040

Jin Lind.

Shanghai Ping Liao Frading.

## **Distributor Wanted**

#### **Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com