

ArChine Arcsyn HTG 300

Introduction:

The product uses a special synthetic thickener thickening and add extreme pressure anti-wear, anti-rust, antioxidant and other additives to refine.

The product has excellent heat resistance and oxidation resistance to prevent oil loss when running at high temperature.

The product has excellent extreme pressure, anti-wear performance and carrying capacity, can be long-lasting reduction of gear wear.

It has strong adhesion can over high speed centrifugal force , not easily be cast off at high speed.

Application:

It applies to worm lubrication and noise reduction in high temperature, high-speed, high-load working condition. And it also applies to electrical gear and bearing, such as steel-making blast-furnace stirring, blast furnace Road, ladle crane and other parts of lubrication.

Operating Temperature Range: -20~300℃

Technical Data:

| | Quality indicators | Method |
|---|---------------------------------|----------------------------|
| Drip point, °C≥ | 340 | GB/T3498 |
| Penetration, 0.1mm | 265-295 | GB/T 269 |
| Corrosion (T ₂ Copper, 100℃,24h) | Copper no green or black change | GB/T 7326 Second method |
| Water Loss (38℃, 1h,Level ≤ | 5 | SH/T 0109 |
| Evaporation (99℃, 22h), % ≤ | 2.0 | GB/T7325 |

Distributor Wanted

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

| | | |
|--|-------|-----------|
| Oxidation stability; Pressure drop; MPa ≤ (99℃, 100h, 0.760MPa) | 0.070 | SH/T 0325 |
| Four-ball Wear, Sintering load, ≤ | 4000 | SH/T 0202 |

Distributor Wanted

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com