

ArChine Arcsyn HTG 400

Introduction:

The product uses a special synthetic thickener thickening and add extreme pressure anti-wear, anti-rust, antioxidant and other additives to refine.

The product has excellent heat resistance and oxidation resistance to prevent oil loss when running at high temperature.

The product has excellent extreme pressure, anti-wear performance and carrying capacity, can be long-lasting reduction of gear wear.

It has strong adhesion can over high speed centrifugal force , not easily be cast off at high speed.

Application:

It applies to worm lubrication and noise reduction in high temperature, high-speed, high-load working condition. And it also applies to electrical gear and bearing, such as steel-making blast-furnace stirring, blast furnace Road, ladle crane and other parts of lubrication.

Operating Temperature Range: -40~400℃

Technical Data:

Items	Quality indicators	Method
Drip point, °C ≥	340	GB/T3498
Penetration, 0.1mm	265-295	GB/T 269
Corrosion (T ₂ Copper, 100°C,24h) Level	Copper no green or black change	GB/T 7326 Second method
Water Loss (38°C, 1h) ,Level ≤	5	SH/T 0109
Evaporation (99°C, 22h), % ≤	2.0	GB/T7325

Distributor Wanted

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

Oxidation stability; Pressure drop; MPa \leq (99°C, 100h, 0.760MPa)	0.070	SH/T 0325
Four-ball Wear, Sintering load, N \geq	4000	SH/T 0202

Shanghai PingYiao Trading CO., Ltd.

Distributor Wanted

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: Xuhui District, Shanghai Caoyi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com