

**ArChine Addform SIB 1008****Sulfurized Isobutylene****Description**

ArChine Addform SIB 1008 is an additive including sulfur prepared from sulfur or mono sulfur chloride and isobutylene. ArChine Addform SIB 1008 provides the lubricants with extreme pressure and antiwear property, and can be widely used for blending gear oils, and industrial oils, etc.

**Special features**

- Excellent extreme pressure abrasion resistance
- Fine oil solubility
- Lower copper corrosion

**Applications**

Used for blending various medium and high grade gear oils;

Used for blending antiwear hydraulic oils;

Used for blending cutting oils;

Used for blending lubricating grease;

The dosage: 1.5-5.0%

**Characteristics**

Item	Typical value
Density (20°C), (ASTM D1298), kg/m <sup>3</sup>	1150
Flash point (COC), (ASTM D92), °C	100
Kinematic viscosity (100°C), (ASTM D445), mm <sup>2</sup> /s	8.0
S, (ASTM D129), m%	44.0
Copper corrosion (121°C, 3h), (ASTM D130)	3

**Points for Attention**

ArChine Addform SIB 1008 is packed in metal drums of 200 litres. Store in dry,

**Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

**ARCHINE**

**Shanghai PingYiao Trading CO., Ltd.**

clean and well ventilated warehouses.

Shanghai PingYiao Trading CO., Ltd.

**Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)