

### GB-9639-125

#### Lubricant for Propane Refrigeration Compressor

##### Description

GB-9639-125 is blend of polyalkylene glycols with unique additives that is specifically designed for use in natural refrigerants such as propane and butane. The ability of GB-9639-125 lubricant to withstand dilution by hydrocarbon and other compressed gas is particularly advantageous in flooded screw compressors.

GB-9639-125 is an ideal fluid for these natural refrigerants such as propane and butane due to its very low pour point, high viscosity index, excellent solubility and superior resistance against viscosity dilution.

##### Attributes

- Specifically designed for use in refrigeration systems requiring PAG lubricants
- Excellent film strength and anti-wear properties for better protection of compressor parts
- Resists viscosity dilution
- Reduced hygroscopic tendencies
- Very high viscosity index for better lubrication and seal protection at extreme temperatures
- Excellent thermal and oxidative stability leading to longer fluid life and extended oil drain intervals
- Increased protection against rust, corrosion, carbon and varnish
- Very high flash points and auto-ignition points for added safety
- Non-toxic/non-hazardous

##### Applications

- Propane refrigeration compressor lubrication.
- Natural gas and other light hydrocarbon compressor applications.

##### Typical Properties\*

Appearance	Colorless clear liquid
Density@20℃ , g/cm <sup>3</sup>	0.992
Viscosity@40℃ , mm <sup>2</sup> /s	124.1
Viscosity@100℃ , mm <sup>2</sup> /s	21.61
ViscosityIndex	200
Flash Point(COC), °C	231
Fire point, °C	249

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yinhai Building, No.250, Caoxi Road,Xuhui District , Shanghai 200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

Pour Point, °C	-39
Copper Corrosion, 100°C, 3hr	1grade
Foam Characteristic, 24°C	25/0

\* The above data is typical data, not as product specifications.

Shanghai PingYiao Trading CO., Ltd.

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yinhai Building, No.250, Caoxi Road,Xuhui District , Shanghai 200235  
P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)