SX-3309-220

Lubricant for Propane Refrigeration Compressor

Description

SX-3309-220 is blend of polyalkylene glycols with unique additives that is specifically designed for use in natural refrigerants such as propane and butane. The ability of SX-3309-220 lubricant to withstand dilution by hydrocarbon and other compressed gas is particularly advantageous in flooded screw compressors.

SX-3309-220 is an ideal fluid for these natural refrigerants such as propane and butane due to its very low pour point, high viscosity index, excellent solubility and superior resistance against viscosity dilution.

Attributes

- Specifically designed for use in refrigeration systems requiring PAG lubricants
- Excellent film strength and anti-wear properties for better protection of compressor parts
- Resists viscosity dilution
- Reduced hygroscopic tendencies
- Very high viscosity index for better lubrication and seal protection at extreme temperatures
- Excellent thermal and oxidative stability leading to longer fluid life and extended oil drain intervals
- Increased protection against rust, corrosion, carbon and varnish
- Very high flash points and auto-ignition points for added safety
- Non-toxic/non-hazardous

Applications

- Propane refrigeration compressor lubrication.
- Natural gas and other light hydrocarbon compressor applications.

Typical Properties*

Appearance	Light yellow liquid
Density@ 20° C, g/cm ³	0.989
Viscosity@40°C, mm ² /s	209.8
Viscosity@100°C, mm ² /s	35.07
ViscosityIndex	216

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai 200235

P.R.China

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209
Website: www.pingyiao.com E-mail: info@pingyiao.com

SYNOLEX

Shanghai PingYiao Trading CO., Ltd.

Flash Point(COC), °C	240
Fire point, °C	258
Pour Point, °C	-39
Copper Corrosion, 100℃, 3hr	1
Foam Characteristic, 24°C	30/0

^{*} The above data is typical data, not as product specifications.

Shanghai Ping Yiao Trading CO.

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai 200235

P.R.China

Fax: 86-21-64705533-209 Telephone helpline: (86)15900706965 Website: www.pingyiao.com E-mail: info@pingyiao.com