

ArChine Arclith LTB 60

Description

ArChine Arclith LTB 60 is a low temperature grease. It contains many additives.

ArChine Arclith LTB 60 has many advantages, for example: water resistant, corrosion resistant, low temperature performance, and so on.

Application

ArChine Arclith LTB 60 suits for filling gearbox casing, spur gears and bevel gear drives, and worm gear pairs and similar industrial gears as well as guiding mechanisms

ArChine Arclith LTB 60 is also suited for central lubricating installations of utility vehicles as well as for outside working units having long tubing.

Operation temperature: -60°C~120°C

Technical Data

ArChine Arclith LTB 60	Unit	Test method
Worked penetration, 0.1mm	265-295	GB/T 269
Drop point, °C ≥	170	GB/T 4929
Corrosiveness to Copper (T ₂ Copper, 100°C, 24h)	No change	GB/T 7326 Second method
Water washout characteristics (38°C, 1h), % ≤	10	SH/T 0109
Evaporation (99°C, 22h), % ≤	2.0	GB/T 7325
Oxidation stability Pressure Drop, Mpa ≤ (99°C, 100h, 0.760MPa)	0.070	SH/T 0325
Oil separation (100°C, 24h), % ≤	8	SH/T 0324
Impurity (microscope), /cm ³ Above 10 um ≤ Above 25um ≤ Above 75um ≤ Above 125um ≤	5000 3000 500 0	SH/T 0336

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

Viscosity (-40℃, 10S ⁻¹) , Pa·S	≤	2000	SH/T 0048
--	---	------	-----------

Shanghai PingYiao Trading CO., Ltd.

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com