

**ArChine Syngear POE 56****Fully synthetic high temperature gear lubricants****Description**

ArChine Syngear POE 56 high temperature lubricant is formulated with synthetic base oil (POE) and multiple efficient additives designed primarily for high temperature equipments. It's suitable for use in industrial gearboxes with high thermal and oxidative stability requirements, roller and plain bearings that are exposed to high loads, and in particular for large systems with circulation lubrication systems.

**Performance**

- ◆ Excellent high temperature oxidation and thermal stability reducing carbon residue formation and prolong lubricant life.
- ◆ Superior antiwear property, prevent rust and corrosion, prolong service life of equipment.
- ◆ Extremely low volatility resulting in less oil consumption and long life.
- ◆ Compatible with mineral oil, don't need special system design.
- ◆ Maintain a clean operating environment owe to clean function.
- ◆ Contain no chlorine and heavy metal, be of biodegradable, green lubricant.

**Applications**

Suitable for lubrication and protection of closed industrial gear exposed to high temperature, medium to high speed or medium to heavy load, sliding and rolling bearing, especially for full range of worm and gears.

ArChine Syngear POE synthetic gear oils can be continuously used in high temperature environment more than 180°C.

**Typical Properties**

Appearance	Yellow
Viscosity @40°C, cSt	55.7
Viscosity @100°C, cSt	7.9
Viscosity index	108
Density@ 20°C, g/cm <sup>3</sup>	0.973
Flash point, °C	284
Fire point, °C	302
Pour point, °C	-42

**Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai 200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

# **ARCHINE**

**Shanghai PingYiao Trading CO., Ltd.**

Total acid number, mg KOH/g	0.57
Copper corrosion, 3h/100°C	1b
RBOT@150°C, min	1410
Noack@250°C, 60min, %	1.2

These technical data are based on average test results. Minor deviations may occur from case to case.

Shanghai PingYiao Trading CO., Ltd.

## **Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai  
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)