

ArChine Base Polymers

Product Description

ArChine base stocks are polyalkylene glycols (PAGs), which are polymers of ethylene oxide and propylene oxide described with the generalized formula:

ArChine Synfluid PAG 50-A series are alcohol-started base stocks containing equal amounts, by weight, of oxyethylene and oxypropylene groups with a single terminal hydroxyl group. They are water soluble at ambient temperature and are available in a variety of molecular weights and viscosities.

ArChine Synfluid PAG 75-W series are diol-started base stocks containing 75 weight percent oxyethylene and 25 weight percent oxypropylene groups with two terminal hydroxyl groups. They are water soluble at temperatures below 75°C and are available in a variety of molecular weights and viscosities.

ArChine Synfluid PAG P series are alcohol-started base stocks of all oxypropylene groups ($m=0$) with one terminal hydroxyl group. They are water insoluble and available in a variety of molecular weights and viscosities.

Product Application

1. ArChine Synfluid PAG 50-A- series

- For Metalworking Fluids
- For Gear & Bearing Oil
- For Release agent for rubber
- For Textile Fiber Lubricant
- ArChine Synfluid PAG 50-A-460/680/1000 for defoaming

2. ArChine Synfluid PAG 75-W- series

- For Water-Glycol Hydraulic Fluid
- For Metalworking Fluids
- For Release agent for rubber
- For Textile Fiber Lubricant
- ArChine Synfluid PAG 75-W-18000/75-W-55000 for Quenching fluid

3. ArChine Synfluid PAG P- series

- For Industrial Lubricants
- ArChine Synfluid PAG P-120/220/320 for defoaming

Typical Physical Properties

Product	ISO	Viscosi	SUS	Viscosi	Viscosi	Flash	Pou	Specifi	M.W
---------	-----	---------	-----	---------	---------	-------	-----	---------	-----

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

	Grade	Viscosity Index (VI)	100°F	40°C (cSt)	100°C (cSt)	Point (°C)C OC	Pour Point (°C)	Specific Gravity 20/20°C	M.W
--	-------	----------------------	-------	------------	-------------	----------------	-----------------	--------------------------	-----

Water soluble grades (50%EO & 50%PO)

ArChine Synfluid PAG 50-A-10		97	55	8.3	2.36	124	-62	0.98	270
ArChine Synfluid PAG 50-A-20		165	100	19	4.59	196	-51	1.01	520
ArChine Synfluid PAG 50-A-30	32	197	170	33	7.45	232	-42	1.03	750
ArChine Synfluid PAG 50-A-50		212	260	53	11.1	238	-40	1.03	1100
ArChine Synfluid PAG 50-A-80		220	400	81	16.3	249	-41	1.04	1270
ArChine Synfluid PAG 50-A-100	100	215	-	100	-	235	-50	-	-
ArChine Synfluid PAG 50-A-150	150	230	-	145	28	240	-48	1.05	2000
ArChine Synfluid PAG 50-A-220	220	239	-	217	41	240	-42	1.06	2600
ArChine Synfluid PAG 50-A-460	460	254	2000	440	70.2	249	-32	1.06	2660
ArChine Synfluid PAG 50-A-680	680	269	3520	700	117	243	-29	1.04	3380
ArChine Synfluid PAG 50-A-1000	1000	281	5100	1000	163	230	-36	1.06	4500
ArChine Synfluid PAG 50-A-1500		-	-	1500	233	-	-	1.06	-

Product	ISO Grade	Viscosity Index (VI)	SUS 100°F	Viscosity 40°C (cSt)	Viscosity 100°C (cSt)	Flash Point (°C)C OC	Pour Point (°C)	Specific Gravity 20/20°C	M.W
---------	-----------	----------------------	-----------	----------------------	-----------------------	----------------------	-----------------	--------------------------	-----

Water soluble grades (75%EO & 25%PO)

ArChine Synfluid PAG 75-W-60	100	184	450	60	19.6	240	-15	1.10	980
ArChine Synfluid PAG 75-W-130		200	-	130	-	230	2	1.05	1400
ArChine Synfluid PAG 75-W-270		207	-	270	41.3	250	-7	1.09	2500
ArChine Synfluid PAG 75-W-2000		310	-	2000	295	-	1.1	-	-
ArChine Synfluid PAG 75-W-17000		414	90,000	17,000	2545	265	4.4	1.09	12000

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

<u>ArChine</u>	<u>Synfluid</u>	<u>PAG</u>		414	-	18,000	2,540	245	6	1.09	1500 0
<u>75-W-18000</u>											
<u>ArChine</u>	<u>Synfluid</u>	<u>PAG</u>		430	-	55,000	7,900	240	6	1.09	3000 0
<u>75-W-55000</u>											
ArChine	Synfluid	PAG		500	-	72,000	9,500	235	8	1.09	3900 0
75-W-70000											
ArChine	Synfluid	PAG		-	380,000	-	11,685	239 (闭杯)	-16	1.10	-
75-W-77000											
ArChine	Synfluid	PAG		500	-	100,000	14,000	235	8	1.09	5200 0
75-W-100K											

Product	ISO Grade	Viscosity Index (VI)	SUS 100°F	Viscosity 40°C (cSt)	Viscosity 100°C (cSt)	Flash Point (°C) OC	Pour Point (°C)	Specific Gravity 20/20°C	M.W.
---------	-----------	----------------------	-----------	----------------------	-----------------------	---------------------	-----------------	--------------------------	------

Water insoluble grades (100%PO)

ArChine Synfluid PAG P-10	10		65	11	2.73	221	-57	0.96	340
<u>ArChine Synfluid PAG P-32</u>	32	169	165	33	6.7	208	-60	0.98	790
ArChine Synfluid PAG P-46	46	188	250	50	9.86	274	-51	0.99	1100
ArChine Synfluid PAG P-68	68	190	285	61	10.8	235	-40	0.99	1020
<u>ArChine Synfluid PAG P-80</u>		190	385	76	13.9	211	-52	0.99	1350
ArChine Synfluid PAG P-100	100	196	525	100	18.4	238	-34	0.98	1420
ArChine Synfluid PAG P-120		200	625	120	21.4	232	-32	0.98	1560
ArChine Synfluid PAG P-220	220	214	1145	230	28.9	235	-29	0.93	2080
<u>ArChine Synfluid PAG P-320</u>	320	219	-	330	51.7	225	-32	1.00	2370

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: (86)15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com