

ArChine Synester BNN 1800

High Performance Synthetic Gear Oil

Product Description

ArChine Synester BNN 1800, fortified with micron scale Boron Nitride powder, is formulated with polyolester fluid and additives. It can be used for lubricating gears exposed to low speed, heavy load and impact load.

ArChine Synester BNN 1800 can provide excellent wear resistance, extreme pressure and assist in load carrying. This product will help to reduce gear pump leak and maintenance time and downtime. It can greatly prolong the service life of equipment and reduce maintenance costs. Boron Nitride powders can continue to provide continuous, clean solid lubrication after the base oil exhausted.

Benefits

- ◆ Excellent high temperature oxidation and thermal stability, very low volatile and less oil consumption
- ◆ Excellent resistance to wear and rust corrosion, provide better protection for equipment;
- ◆ No carbon residues form under high temperature, and have excellent high-temperature lubricity;
- ◆ Small friction coefficient, strong carrying capacity, having the function of jointing and running-in.

Typical Properties

Viscosity@40°C, cSt, GB/T265	1869
Viscosity @100°C, cSt, GB/T265	187.9
Viscosity index (VI) ≥,GB/T1995	226
Pour point °C, ≤, GB/T3535	- 9
Flash point°C, ≥, GB/T267	276
Copper corrosive, 100°C, 3h	1

Recommended Applications

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road,Xuhui District , Shanghai
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com

ARCHINE

Shanghai PingYiao Trading CO., Ltd.

Recommended for bearing and gear devices exposed to high temperature, heavy load and impact load.

*Typical data shall not be used as product specifications.

Shanghai PingYiao Trading CO., Ltd.

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Address: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: www.pingyiao.com

E-mail: info@pingyiao.com