

Shanghai PingYiao Trading CO., Ltd.

ArChine Synester BNN 280

High Performance Synthetic Gear Oil

Product Description

ArChine Synester BNN 280, fortified with micron scale Boron Nitride powder, is formulated with polyolester fluid and additives. It can be used for lubricating gears exposed to low speed heavy load and impact load.

ArChine Synester BNN 280 can provide excellent wear resistance, extreme pressure and assist in load carrying. This product will help to reduce gear pump leak and maintenance time and downtime. It can greatly prolong the service life of equipment and reduce maintenance costs. Boron Nitride powders can continue to provide continuous, clean solid lubrication after the base oil exhausted.

Benefits

- ◆ Excellent high temperature oxidation and thermal stability, very low volatile and less oil consumption
- ◆ Excellent resistance to wear and rust corrosion, provide better protection for equipment;
- ◆ No carbon residues form under high temperature, and have excellent high-temperature lubricity;
- ♦ Small friction coefficient, strong carrying capacity, having the function of jointing and runningin.

Typical Properties

Density, 20°C g/cm ³	0.99
Viscosity@40°C, cSt, GB/T265	300.5
Viscosity @100°C, cSt, GB/T265	37.5
Viscosity index (VI) ≥,GB/T1995	175
Pour point °C, ≤, GB/T3535	-27
Flash point°C, ≥, GB/T267	284
Copper corrosive, 100°C, 3h	1

Recommended Applications

Recommended for bearing and gear devices exposed to high temperature, heavy load and impact load.

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533 Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai

200235 P.R.China

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com



Shanghai PingYiao Trading CO., Ltd.

*Typical data shall not be used as product specifications.

Shanghai Ping Yiao Trading CO.

Distributor Wanted

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533 Adress: A1207, Yinhai Building, No.250, Caoxi Road, Xuhui District, Shanghai

200235 P.R.China

Telephone helpline: (86)15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com