

## **CP-9078-150**

### **PRODUCT DESCRIPTION**

CP-9078 series products are custom formulated lubricants specifically designed for use under the severe, demanding conditions encountered in industrial machinery. They are formulated to give excellent lubricity and antiwear characteristics.

CP-9078 series products are specially formulated to adhere to metal surfaces and prevent throwing off or dripping. This adhesive/cohesive feature makes it ideal in applications where oil control is necessary such as in textile mills and chain applications. These same features provide excellent mist control for air-line lubricated applications and maximize their effectiveness.

CP-9078 series products are based on highly refined, hydrotreated dewaxed paraffinic oil.

This special refining coupled with state of the art additive technology results in performance improvements beyond other mineral oil. Among these are:

- Exceptional oxidative stability
- Long life
- Low evaporation loss
- Less frictional drag
- Less downtime
- Improved economy
- Viscosity stability
- Consistent quality
- Thermal & hydrolytic stability
- Improved performance
- Rust and corrosion inhibited
- Lower equipment maintenance

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

- Resistance to carbon buildup and low sludging tendency

**TYPICAL PROPERTIES\***

**CP-9078-150**

Viscosity@40°C,cSt, ASTM D445	149
Viscosity @100°C,cSt	15.3
Viscosity @100°F	169.2
Viscosity @210°F	15.9
Viscosity Index ASTM D2270	100
Density 1b/gal, 60°F °F	7.26
Pour point, °F (°C)	20(-6)
Flash point C.O.C., °F (°C) ASTM D92	515(268)
Fire point C.O.C., °F (°C) ASTM D92	540(282)
Specific Gravity, ASTM D1298	0.872

\*These values are not intended for use in preparing specifications

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)