

## **CPI COMP OIL 68**

### **PRODUCT DESCRIPTION**

CPI Comp Oil series products are custom-formulated lubricants specifically designed for long life under the severe, demanding conditions normally encountered in recirculating systems such as rotary screw compressors.

CPI Comp Oil series products are based on highly refined “semi-synthetic”, hydro-treated dewaxed paraffinic oil. This special refining coupled with state-of-the-art additive technology results in performance improvements beyond conventional mineral oils and many synthetic oils. Among these are:

- Exceptional oxidative stability
- Long life
- Rust and corrosion inhibited
- Improved economy
- Thermal and hydrolytic stability
- Consistent quality
- Lower equipment maintenance
- Viscosity stability
- Less frictional drag less downtime
- Improved performance
- Resistance to carbon build-up & low sludging tendency
- Low evaporation loss

<b>TYPICAL PROPERTIES*</b>	<b>Comp Oil 68</b>
Viscosity@40°C ,cSt,ASTM D445	68
Viscosity@100°C ,cSt	8.9
Viscosity@100°F ,cSt	76

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

Viscosity@210°F ,cSt	9.1
Viscosity Index ASTM D2270	104
Density ,lbs/gal, 60°F	7.22
Pour Point °F (°C)ASTM D97	-38(-39)
Flash Point,C.O.C., °F (°C)ASTM D92	440(227)
Fire Point ,C.O.C., °F (°C)ASTM D92	470(243)
Specific Gravity, ASTM D1298	0.868
Water Content	40ppm
Demulsibility, ml oil/ml water/ml emulsion (separation time, min.)	40-40-0(2)

\*These values are not intended for use in preparing specifications.

Shanghai PingYiao Trading CO., Ltd.

Address: Xuhui District, Shanghai Caoyi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)