

SOLEST*-220

Typical Properties

Viscosity, cSt,

40°C	215.9
100°C	20.8
210°F	24.5
100°F	223.1
Viscosity Index	113
Density, lbs/gal	7.75
Flash Point °C(°F).....	271(520)
Fire Point °C(°F).....	318(605)
Pour Point °C(°F).....	-27(-17)
Specific Gravity	0.955
Dielectric Strength (ASTM D-877)	41.8 kv

*The Trademark and Service Mark CPI and the Trademark SOLEST are registered in the United States (CPI[®], SOLESE[®]), and in a number of other countries.

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com