

# SOLEST\*-320\*

## Typical Properties

### Viscosity, cSt,

|                         |          |
|-------------------------|----------|
| 40°C .....              | 319.40   |
| 100°C .....             | 22.84    |
| 210°F .....             | 23.58    |
| 100°F .....             | 368.60   |
| Viscosity Index .....   | 88       |
| Density, lbs/gal .....  | 8.00     |
| Flash Point °C(°F)..... | 279(535) |
| Fire Point °C(°F).....  | 296(565) |
| Specific Gravity .....  | 0.960    |

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)