

SOLEST*-35*

Typical Properties

Viscosity, cSt,

40 °C	36.7
100 °C	5.96
210°F	6.10
100°F	40.49
Viscosity Index	106
Density, lbs/gal	7.85
Pour Point °C(°F).....	-45(-49)
Flash Point °C(°F).....	235(455)
Fire Point °C(°F).....	260(500)
Specific Gravity	0.942

*The Trademark and Service Mark CPI and the Trademark SOLEST are registered in the United States (CPI[®], SOLESE[®]), and in a number of other countries.

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com