

SOLEST*-370*

Typical Properties

Viscosity, cSt,

40 °C	385.96
100 °C	29.23
210°F	30.22
100°F	442.88
Viscosity Index	105
Density, lbs/gal	7.95
Pour Point °C(°F).....	-21 (-6)
Flash Point °C(°F).....	302(575)
Fire Point °C(°F).....	354(670)
Specific Gravity	0.955
Dielectric Strength , ASTM D-877	47.7 kv

*The Trademark and Service Mark CPI and the Trademark SOLEST are registered in the United States (CPI[®], SOLESE[®]), and in a number of other countries.

Shanghai PingYiao Trading CO., Ltd.

Adress: Xuhui District, Shanghai Caoxi Yin Hai Building, A1207 Room, No. 250

Telephone helpline: 15900706965

Website: www.pingyiao.com

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: info@pingyiao.com