

## Shanghai Jichuan Trading

## Glanz-Zink-Spray (Bright Zinc Spray)

**DESCRIPTION** 

Bright Zinc Spray is an active means of cathodic corrosion protection. The resistant, flexible, heat-resistant zinc film which is produced protects iron and steel components from rust and corrosion. Bright Zinc Spray can also be used as the only means of corrosion protection.

**PROPERTIES** 

lasting corrosion protectionsmooth, pore-free filmhigh zinc content

- electrically conductive

- quick drying and can be painted over

high heat resistancespot weldable

TECHNICAL DATA

Colour : grey, bright Zinc purity : > 99 %

Proportion of zinc :> 99 % (as a dry film)
Binder : special resins
Temperature range : up to 490 °C
Density : 1.95 g/cm³
: 5-7 min. dust dry

20-30 min. touch dry

can be painted over after 8 hours

Propellant : propane/butane

**APPLICATION** 

Used to protect iron and steel components from rust and corrosion. Suitable for repairing all damaged forms of galvanising (hot-dip, flame spraying and electroplated zinc). Bright Zinc Spray can also be used as the only means of weather-resistant corrosion protection.

INSTRUCTIONS

Shake can vigorously for at least 1 minute before use. Spray onto clean, dry, degreased metallic surfaces. Can be painted over after 8 hours. Layer thickness of the zinc film dry after a single spraying: 25-35  $\mu$ m.

After use, clear spray nozzle by inverting can and spraying until only the propellant emerges.

AVAILABLE

PACK SIZE Bright Zinc Spray 400 ml Aerosol, Part no. 1640

Shanghai Jichuan Trading Co., Ltd.

Add: No 1201, Yinhai Building, Caoxi Road, Tel: (86) 021-64820099

Xuhui District, Shanghai

 24h Hotline: 15900706965
 Fax: (86) 021-64513829

 Website: www.pingyiao.com
 E-mail: info@jichuan.sh.cn



## Shanghai Jichuan Trading

Shangt Le

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yinhai Building, Caoxi Road,

Xuhui District, Shanghai

24h Hotline: 15900706965 Fax: (86) 021-64513829

Website: www.pingyiao.com E-mail: info@jichuan.sh.cn

Tel: (86) 021-64820099