

## Shanghai Jichuan Trading

## Pipe Sealant

**DESCRIPTION** 

Pipe Sealant is a medium-strength, high-viscosity, dimethylacrylate ester-based adhesive which does not contain solvents and cures in the absence of oxygen.

**PROPERTIES** 

cures fast

excellent wetting properties

medium strength

no liquid residues outside the bonded screwed joint

cures in the absence of oxygen replaces hemp and pastes

simple to use

**TECHNICAL DATA** 

Colour

**Basis** dimethylacrylate ester Storage life at least 2 years (unopened)

Cure time at room temp. hand strength 5 -15 minutes

function strength 2-5 hours final strength 12 hours

Strength class medium strength 1.1x10<sup>3</sup> kg/m<sup>3</sup> Density Thread sizes all threads Thread friction value 0.17

Strengths when cured

Breakaway torque 16 Nm Compressed shear strength 15 N/mm<sup>2</sup>

Operating temperature range : -60 °C to +150 °C

**APPLICATION** 

Pipe Sealant is suitable for bonding and sealing pipe threads and screwed joints. Pipe Sealant was developed for sealing screwed connections on brake systems, fuel systems, oil circuits of engines, hydraulic systems and water circuits etc. In Germany, this has not been approved for use on domestic gas installations.

INSTRUCTIONS

The components to be sealed must be free from contaminants such as oil films, dirt, paint or other coating materials. The optimum seal is achieved by roughening the surfaces. The sealant has been formulated so that the joint can be unscrewed using the appropriate tool, without damaging the thread.

AVAILABLE PACK SIZE

Pipe Sealant Part no. 3808 10 g bottle

Shanghai Jichuan Trading Co., Ltd.

Add: No 1201, Yinhai Building, Caoxi Road, Tel: (86) 021-64820099

Xuhui District, Shanghai

24h Hotline: 15900706965 Fax: (86) 021-64513829 Website: www.pingyiao.com E-mail: info@jichuan.sh.cn



## Shanghai Jichuan Trading

nghai "

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yinhai Building, Caoxi Road,

Xuhui District, Shanghai

24h Hotline: 15900706965

Website: www.pingyiao.com

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: info@jichuan.sh.cn