



# Shanghai Jichuan Trading

## Wachs-Unterboden-Schutz anthrazit (Aerosol) Wax Underseal anthracite (aerosol)

### DESCRIPTION

Wax Underseal anthracite (aerosol) is a corrosion inhibitor which forms a continuous protective film when dry, thanks to the waxes and resins contained in it. The material can be finely sprayed and is characterized by high rigidity. The dried film has good adhesion and corrosion-protection properties. Wax underseal anthracite (aerosol) is mainly used for repairing all underseal coatings which are applied at the factory. The product protects all car underbodies.

### PROPERTIES

- can be sprayed finely
- continuous film with thin coating thicknesses
- quick drying
- rigid
- very good processing characteristics
- for aftertreatment of barely accessible areas
- for supplementing protective coatings based on PVC, rubber-resin, rubber-bitumen as well as wax-coated underbodies.

### TECHNICAL DATA

Base	:	wax/resin	
Color	:	anthracite	
Odor	:	characteristic	
Density at 20 °C	:	0.87	g/cm <sup>3</sup>
Propellant	:	propane/butane	
Solids content	:	Approx. 52 %	
Coating thickness with 2 - 3 cross patterns	:	100 – 200	µm dry film
Drying time	:	1-2	hours
Heat resistance	:	-30 °C - +90 °C	
Processing temperature	:	15 °C - 25 °C	
Risk of frost damage	:	no	
Recommended storage temperature	:	5 °C - 25 °C	
Storage time	:	24 months	
Corrosion resistance	:		
Salt-spray test ASTM B 117	:	above 1000	hours

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road, Xuhui District, Shanghai

24h Hotline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: [info@jichuan.sh.cn](mailto:info@jichuan.sh.cn)



# Shanghai Jichuan Trading

## APPLICATIONS

For the repair, aftertreatment or supplementing of protective coatings based on PVC rubber-resin, rubber-bitumen as well as wax-coated underbodies in relatively inaccessible areas. Selective application and repairs after accident repairs.

## APPLICATION

The surfaces which are to be treated with wax underseal anthracite (aerosol) must be thoroughly cleaned beforehand. Rust must be removed. The surfaces must be dry and free of dirt and grease and extensively free of dust.

The material is best suited for use at room temperature. Shake can vigorously. When the ball has worked loose, continue to shake the can for a further minute. Hold the can vertically when spraying and spray thinly at a distance of about 20 - 30 cm from the surface. The resistance to abrasion and corrosion increases with increasing coating thickness. For this reason, the spraying process should be repeated once or twice after a short flash-off period.

**After use, the can must be inverted and sprayed until the valve is clear of the product, with only propellant escaping.**

### Note

Do not spray material onto moving parts and hot components such as mechanical joints, the engine, gearbox, drive shaft, exhaust pipe, catalytic converter and brake systems.

## AVAILABLE PACK SIZE

Wax Underseal  
anthracite

500 ml aerosol Part. no. 6100

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yinhai Building, Caoxi Road, Xuhui District, Shanghai

24h Hotline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Fax: (86) 021-64513829

E-mail: [info@jichuan.sh.cn](mailto:info@jichuan.sh.cn)



# Shanghai Jichuan Trading

Shanghai Jichuan Trading Co., Ltd.

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yinhai Building, Caoxi Road, Xuhui District, Shanghai

24h Hotline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Fax: (86) 021-64513829

E-mail: [info@jichuan.sh.cn](mailto:info@jichuan.sh.cn)