



Shanghai Jichuan Trading

Hohlraumversiegelung Weiß/transparent (Cavity Protection white/transp.)

DESCRIPTION

Solvent-based corrosion inhibitor for cavity protection with a high solids content. A thixotropic liquid with good atomizing properties which is capable of reaching areas difficult to access, reaches into and wets narrow spaces between metal panels and displaces moisture. The product contains a high proportion of rust inhibitors and can be used at low temperatures above 10 °C. Creep behavior is improved if the product and bodywork are at room temperature. On drying completely, the product forms a plastic, water repellent waxy film.

PROPERTIES

- High creep
- Short follow-up time
- Ideal for rust protection on welded body components
- good heat resistance

TECHNICAL DATA

Base	:	wax
Color	:	white/transparent
Odor	:	solvent-type
Form	:	liquid
Density at 20 °C	:	0.85 g/cm ³
Flash point	:	26 °C
Boiling point	:	135 °C
Viscosity at 20 °C	:	30 seconds
Solids	:	47 +/- 2%
Hazard class	:	all
Drying time	:	approx. 1 hour
Salt-spray test ASTM B 117	:	more than 500 hours

APPLICATIONS

Ideally suitable for all body cavities such as sills, doors, struts and fenders etc.

APPLICATION

In the workshop, the product is mainly used for protection of the inner surfaces of cavities, for supplementing existing cavity protection in new vehicles and for the aftertreatment of cavity protection after 2 - 3 years and after accident repairs.

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road, Xuhui District, Shanghai

24h Hotline: 15900706965

Fax: (86) 021-64513829

Website: www.pingyiao.com

E-mail: info@jichuan.sh.cn



Shanghai Jichuan Trading

**AVAILABLE
PACK SIZE**

Cavity protection	1 l can	Part. no. 6116
	10 l	Part. no. 6118

Processing equipment

Pressure-feed spray gun for cavities Part. no. 6226

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road, Xuhui District, Shanghai

24h Hotline: 15900706965

Website: www.pingyiao.com

Fax: (86) 021-64513829

E-mail: info@jichuan.sh.cn