

### Shanghai PingYiao Trading CO., Ltd.

# **LOSOID CRL 16615**

#### Introduction

The lubricant described in this data sheet belongs to the LOSIMOL Cleanroom
Lubricant Series, especially developed for the requirements of the cleanroom
technology (e.g. semiconductor manufacturing). This means that the cleanroom
lubricants not only correspond to usual tribolo-gical characteristics but also to the
specific requirements of cleanroom technology like number and size of
particles. Therefore LOSIMOL Cleanroom Lubricants are classified according to
these two items.

### Clearoom Characteristics

The determination of the results of the particle emission behaviour and particle size distribution has been done under standardised conditions. A wafer positioning unit of a semiconductor inspection equipment served as a test stand.

## General Technical Data Regarding LOSOID CRL 16615:

Penetration Worked(Consistency) 260/280

Apparent Dynamic Viscosity mp a.s(cp) abt.3.500cp

Ductility weak

Evaporation Loss 1  $2\% - 16h/70^{\circ}$ C

Spreading Behaviour Sp =  $55/70^{\circ}$ C

Operating Temperature Range abt. -45 °C/+85 °C

Resistant Plastics PA PC POM PS

PPO ABS SAN

Shanghai PingYiao Trading CO., Ltd. Tel: 86-21-64705533

Adress: Xuhui District, Shanghai Caoxi Yinhai Building, A1207 Room, No. 250

Telephone helpline: 15900706965 Fax: 86-21-64705533-209 Website: www.pingyiao.com E-mail: info@pingyiao.com