



## *meguinfo*

Article no. 2200.010

Issue date: 01.09

### **megol Hydraulikoel HLP 10 AF**

HLP AF hydraulic oils are mineral base oils offer excellent EP properties and outstanding ageing and corrosion stability. As a result of their special additives they are capable of absorbing certain volumes of water without turbidity and without any negative effect on their other properties. Their foaming properties and air separation capacity are adjusted for optimal performance. Thanks to their specific properties, HLPD hydraulic oils are ideal for hydraulic systems that are susceptible to condensation, such as machine tools, building machinery, etc.

Approvals / Specifications: Hydraulic Oil DIN 51524 – HLP 10

#### **Characteristic data**

**Approx. values**

ISO viscosity class	DIN 51519		VG 10
Viscosity at -20°C	DIN 51562	mm <sup>2</sup> /s	200
Viscosity at 0°C	DIN 51562	mm <sup>2</sup> /s	50
Viscosity at 40°C	DIN 51562	mm <sup>2</sup> /s	10
Viscosity at 100°C	DIN 51562	mm <sup>2</sup> /s	2.65
Viscosity index	DIN ISO 2909		100
Density at 15°C	DIN 51757	kg/m <sup>3</sup>	880
Flash point	DIN ISO 2592	°C	136
Pour point	DIN ISO 3016	°C	-32
Air separation capacity / 50°C	DIN 51381	min.	2
De-emulsifying capacity / 54°C	DIN 51599	min.	< 10
Ash, oxide	DIN EN 7	g/100 g	0,16
Ash, sulphate	DIN 51575	g/100 g	0,17
Content of asphaltenes	DIN 51595	g/100 g	m.n.n. *)
Content of undissolved substances	DIN 51592	g/100 g	m.n.n. *)
Water content	DIN ISO 3733	g/100 g	m.n.n. *)
Neutralisation index, acid	DIN 51558 Part 1	mg KOH/g	0.2
Corrosive effect on steel	DIN 51585	degree of corrosion	0-B
Corrosive effect on copper		after 1000 h	
	Ageing properties		
	Neutralisation index	Foaming properties	

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road,  
Xuhui District, Shanghai

24h Hotline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: [info@jichuan.sh.cn](mailto:info@jichuan.sh.cn)



# Shanghai Jichuan Trading

DIN 51759	degree of corrosion	1-125 A3
DIN 51587	mg KOH/g	< 2
DIN 51566		S1B-30/0 S2B-50/0 S3B-30/0

\*) m.n.n. = Quantity not detectable

Shanghai Jichuan Trading Co., Ltd.

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yinhai Building, Caoxi Road,  
Xuhui District, Shanghai

24h Hotline: 15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: [info@jichuan.sh.cn](mailto:info@jichuan.sh.cn)