



meguinfo

Artikel Nr. 2292.000

Stand: 99.09

megol hydraulic oil HEES 22 (biologically degradable)

megol hydraulic oil HEES 22 (biologically degradable) is a hydraulic oil based on high quality synthetic esters. The product offers excellent viscosity-temperature properties. It can be used all year round thanks to its excellent low temperature properties. Its EP additives and polar adhesion capacity provide outstanding wear protection and very good protection against rust and corrosion. It is toxicologically safe, completely biologically degradable and miscible with all mineral oil-based products but not water-soluble. megol hydraulic oil HEES 22 (biologically degradable) is particularly suitable for use in the hydraulic systems of equipment that is primarily used outdoors or where there is a high risk of pollution by leakage, such as mobile cranes and excavators for agricultural and forestry use, floating excavators, lock gate hydraulic systems, ski piste equipment, etc.

Specifications/Approvals: Hydraulic oil to VDMA 24568 – HEES 22
 Hydraulic oil to DIN 51524 – HLP 15-46
 Hydraulic oil to DIN 51524 – HVLP 22

Characteristic data

Approx. values

Viscosity at 0 °C	DIN 51562	mm ² /s	140
Viscosity at 40 °C	DIN 51562	mm ² /s	25
Viscosity at 100 °C	DIN 51562	mm ² /s	6.2
Viscosity index	DIN ISO 2909		204
Destiny at 15 °C	DIN 51757	kg/m ³	910
Flash point	DIN ISO 2592	°C	247
Pour point	DIN ISO 3016	°C	-35
Air release behavior at 50 °C	DIN 51381	min.	5
Demulsifying power at 54 °C	DIN 51599	min.	15
Ash, oxide	DIN EN 7	g/100g	< 0.01
Content of asphaltenes	DIN 51595	g/100g	m.n.n.*)
Content of undissolved substances	DIN 51592	g/100g	m.n.n.*)
Water content	DIN ISO 3733	g/100g	m.n.n.*)
Neutralization number, acid	DIN 51558 part 1	mg KOH/g	3.0
Corrosion effect on steel	sealing	DIN 51585	corr.-size
Corrosion effect on Cu	material SRE-	DIN 51759	corr.-size
Foaming property	NBR 1	DIN 51566	

Behavior against

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road,
Xuhui District, Shanghai

24h Hotline: 15900706965

Website: www.pingyiao.com

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: info@jichuan.sh.cn



Shanghai Jichuan Trading

0-A	S1B-30/0	S3B-30/0	
1-100 A3	S2B-50/0		
according to DIN 53538 part 1	volume change	vol.-%	+ 15
after 7 days at 100 °C	hardness change	shore	-8
FZG gear short test	DIN 51354		
Normal test A/8.3/90	damage-strength-grandates		> 12
Vickers pump test	specific gravity change	mg/KWh	< 0.27
Wear according to 250 h	V 105 C		
	ring	mg	50
	wing	mg	8
Biodegradability			
after 21 days	CEC L-33-T-82	%	>95
rating according to water endangering class			1

*) m.n.n. = quantity not detectable

Shanghai Jichuan Trading Co.,Ltd.

Add: No 1201, Yin Hai Building, Caoxi Road,
Xuhui District, Shanghai

24h Hotline: 15900706965

Website: www.pingyiao.com

Tel: (86) 021-64820099

Fax: (86) 021-64513829

E-mail: info@jichuan.sh.cn