

r.*tecc* **Norplex LKP 2** Lithium Complex EP Grease – NGI-Grade 2

Description	r. <i>tecc</i> Norplex LKP 2 is a high performance EP-grease based on high quality mineral oil.		
Application and Properties	 r.<i>tecc</i> Norplex LKP 2 suits for lubrication of roller and friction bearings under extreme pressure load at high temperatures. r.<i>tecc</i> Norplex LKP 2 offers high mechanical stability, good seal up properties against dust and water. Therefore, it suits in most cases for life time lubrication and for the lubrication of oscillating bearings. It is specifically recommended for wheel bearing lubrication in vehicles and trucks. 		
	Advantages: high thermal resistance extremely resistant to oxidation water resistant high stability corrosion resistant high pressure load capacity good adhesiveness 	din	goulit
Technical Data	Thickener		Lithium Complex Seen
	Operating temperature for long-term lubrication		Lithium-Complex-Soap -20 to +150°C
shanghai	Short time admissible temperature peak value Permanent temperatures above 150°	C require regreasing	+200°C at shorter intervals subject to
	thermal load Drop point	ASTM D 2265	> 260°C
	Worked penetration after 60 strokes	ASTM D 217	265 to 295 1/10 mm
	Penetration loss after 100 000 strokes	ASTM D 217	< 30 1/10 mm
	Type of base oil		Mineral oil
	Base oil viscosity at 40° C	ASTM D 445	115 mm²/s
	Water resistance	DIN 51 807-01	1 - 90
	SKF Emcor Test	IP 220/85	Corrosion degree 0/0
	Copper Strip Test	ASTM D 4048	Corrosion degree 1 - 150
	FAG-FE9 - Test	DIN 51821-02-A/ 1500/6000-150	F ₅₀ > 100 h
	Timken Test, well load	ASTM D 2509	50 lbs (222,5 N)
	Designation	DIN 51 502	KP 2 P-20

Subject to modification of the technical data. Please refer to the material safety data sheet for additional information or contact our application engineers.

Edition

10/06

Shanghai Ping Yiao Trading Co., Ltd. TEL: 86 21 6470 5533 24H:15900706965 FAX: 86 21 6482 0538 http:www.pingyiao.com Email:info@pingyiao.com

Rhenus is certified according to ISO/TS 16949, DIN EN ISO 9001, DIN EN ISO 14001 and OHSAS 18001.